

Your Ref: Our Ref: MRK NO. 7043 2136/T3358/12/ID

Enquiries:

J Moagi

Date

(012) 428 7659 2012-09-20

Spectank
Attention: Mr Rey Baartjies
P O Box 391036
Bramley
2018

TESTING TO SANS 1828:2005 MRK NO: 7043

Dear Sir/Madam,

Enclosed, please find our Test Report Number 2136/T3358/12/ID dated 12 September 2012.

As reported in the attached report, full specification tests were conducted on the sample/s submitted. The sample/s complied with the relevant requirements of the above specification for tests done.

Should you require any further information or wish to comment on the test report, please do not hesitate to contact the undersigned.

Yours faithfully

K. Ø. Nefadi

MÁNAGER: CHEMICAL

SABS COMMERCIAL SOC LTD

J Moagl

SABS COMMERCIAL SOC Ltd. Reg. No. 2000/013581/07

Directors: Mr CB Sibisi, Dr B Mehlomakulu, Dr T Demana, Dr MJ Ellman, Mr WK Masvikwa, Ms B Mosako, Mr ME Mkwanazi, Ms WiJ Poulton, Ms W de Witt (Company Secretary). **Website:** www.sabs.co.za **E-mail:** info@sabs.co.za

TEST REPORT



Enquires:

NN Mnculwane

Tel:

(012) 428 6355

Date:

2012-09-12

Report No:

2136/T3358/12/ID

Page:

1 of 2

Spectank
Attention: Mr Rey Baartjies
P O Box 391036
BRAMLEY
2018

TESTING TO SANS 1828 REF MRK NO. 7043

1 SAMPLE DESCRIPTION

Restore, Reoven and Carbsolve.

The samples were received in a condition suitable for testing.

2 SAMPLE SUBMITTED

Sample receipt no.: 9039
Sampling date: 2012/08/23
Sample receipt date: 2012/08/27
Test starting date: 2012/09/10
Test completion date: 2012/09/11

3 TEST REQUESTED

Cleaning chemicals for use in the food industry - SANS 1828: 2005 Edition 1.3.

4 CONCLUSION

The samples comply with the requirements of specification SANS 1828 in respect of corrosion-resistant steel.

TESTING TO SANS 1828 REF MRK NO. 7043

5 TEST RESULTS

Property	Description of sample	*Dilution	*Temperature, ⁰ C	Change in mass, mg/100mm²	Appearance of test strip after testing
Effect on corrosion resistant steel	Restore	Undiluted	25	<0,01	Passes
	Reoven	Undiluted	25	<0,01	Passes
	Carbsolve	6kg/90l	25	<0,01	Passes

^{*}Manufacture's requirements.

6 REMARKS

The cleaning chemical shall not cause pitting, etching, or discoloration of the test strip. Any loss of mass shall not exceed 0,05 mg/100 mm².

7 CONCLUSION

The samples comply with the requirements of specification SANS 1828 in respect of corrosion-resistant steel.

PP Machoga

Test Officer: Industrial Chemistry

ND: Analytical Chemistry

NP Mposula

Authorizing Test Officer: Industrial Chemistry

BSc: Chemistry

This test was performed by SABS Commercial (Pty) Ltd

This report relates only to the specific sample(s) tested herein. It does not imply the SABS mark of approval of the quality and/or performance of the item(s) in question and the test results do not apply to any similar item that has not been tested. (Refer also to the conditions printed on the back of the official test reports.)